

6.4 极压-添加剂-复合包

产品 **Additive EP 16006**

特性 **EP 16006** 是一款不含锌和氯的极压复合包，应用于成型和冷锻油的配方中，用该产品配置的油可以用于大规模螺母和螺栓/螺钉的加工。成品油在模具和金属之间形成稳定的离型膜。该膜耐高温高压。同时也适用于普通钢和不锈钢的加工。该产品包含活性硫，因此不得用于黄色金属。

技术数据		典型	规格		
		数据	最小	最大	
颜色	:	0.8			ACL 014
外观 20°C	:	黄色			
密度 20°C (g/ml)	:	0.942	0.932	0.952	DIN 51 757
粘度 40°C (mm ² /s)	:	121			DIN 51 562-1
总硫分 (wt.%)	:	11.4			calculative
闪点 (°C)	:		100		DIN EN ISO 2719

应用 20-40%EP16006+60-80%石蜡基础油，该配方粘度在 40°C 时调节至约 60mm²/s。

存储 产品可以在室内，无霜，密封的原始包装中存放至少 6 个月。

The data contained herein serve as general information for our customers only and are not binding. The data contained herein have been collected to the best of our knowledge and do not constitute any advice or warranty to our customers for any specific application. It is up to our customer at their own risk to determine the suitability of each product for their individual purposes. The products are sold without any representation, warranty or guarantee either expressed or implied. Our liability is limited to the value of the supplied merchandise.