

### 3.3 其他磺酸盐

#### 产品 **Barium Sulfonate BA 14 A**

**特性** **BA 14 A** 是一款合成的高碱值磺酸钡，拥有高分子量和磺酸盐含量高的特点，故防锈性能非常好。并且由于它自身的高碱性，可以用来中和酸雾。

技术资料	典型数值	规格		
		最小	最大	
密度 15°C (g/ml)	: 1.100	1.000	1.200	DIN 51 757
活性成分(wt.%)	: 61	60	63	ACL-028
矿物油(wt.%)	: 38	36.5	39.5	calculative
水分(wt.%)	: 0.4		0.5	DIN 51 777-1
硫酸灰分 BaSO <sub>4</sub> (wt.%)	: 25	24	26	DIN 51 575
总碱值(mg KOH/g)	: 61	60	65	ACL-006
钡含量 (wt.%)	: 14.4	14.0	15.3	ACL-028
闪点 PMCC (°C)	:	150		DIN EN ISO 2719
平均分子量	: 1027			calculative

**存储** 原装密封条件下在 0°C 到 40°C 之间可以安全存放至少 12 个月。

The data contained herein serve as general information for our customers only and are not binding. The data contained herein have been collected to the best of our knowledge and do not constitute any advice or warranty to our customers for any specific application. It is up to our customer at their own risk to determine the suitability of each product for their individual purposes. The products are sold without any representation, warranty or guarantee either expressed or implied. Our liability is limited to the value of the supplied merchandise.